

## Component - Plastics

E41797

## Guide Information

## TORAY INDUSTRIES INC

NIHONBASHI-MITSUI TOWER, 1-1 NIHONBASHI-MUROMACHI 2-CHOME, CHUO-KU TOKYO 103-8666 JP

## 900

Acrylic/Acrylonitrile Butadiene Styrene (Acrylic/ABS) "Toyolac", furnished as pellets

Color	Min. Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
ALL	1.3	HB	-	-	60	60	60

Comparative Tracking Index (CTI): -

Inclined Plane Tracking (IPT) kV: -

Dielectric Strength (kV/mm): -

Volume Resistivity (10<sup>8</sup> ohm-cm): -

High-Voltage Arc Tracking Rate (HVTR): -

High Volt, Low Current Arc Resis (D495): -

Dimensional Stability (%): -

NOTE - Polyamide (nylon) grades may be prefixed with the letters CM and may employ hyphens in various locations. The designations of ECODEAR products may employ hyphens and/or spaces in various locations. All grades that include ABS, SAN, and/or PC (designations of TOYOLAC or TOYOLAC/PAREL or TORAYCA products) may employ hyphens and/or spaces and may be suffixed with 3 or 4 digits of letters and/or numbers.

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1989-11-13

Last Revised: 2003-10-24

© 2018 UL LLC



## IEC and ISO Test Methods

Test Name	Test Method	Units	Thk (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	1.3	HB75 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	°C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	°C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	°C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	°C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m <sup>2</sup>	-	-
ISO Izod Impact	ISO 180	kJ/m <sup>2</sup>	-	-
ISO Charpy Impact	ISO 179-2	kJ/m <sup>2</sup>	-	-