Need more information? Click Here to go to the iQ™ for Plastics database

Component - Plastics E65424

KUMHO PETROCHEMICAL

KUMHO BLDG 57, 15TH & 16TH FL, 57 SHINMMUNRO, 1-KA, CHONGNO-KU, SEOUL 110-061 KR

ABS-750SW

Acrylonitrile Butadiene Styrene (ABS), furnished as pellets

Min Thk	Flame			RTI	RTI	RTI
(mm)	Class	HWI	HAI	Elec	lm p	Str
1.5	НВ	3	0	60	60	60
3.0	НВ	2	0	60	60	60
	1.5	1.5 HB	1.5 HB 3	1.5 HB 3 0	1.5 HB 3 0 60	1.5 HB 3 0 60 60

Comparative Tracking Index (CTI): 0

High-Voltage Arc Tracking Rate

High Volt, Low Current Arc Resis (D495): 6

Dimensional Stability (%): -

(HVTR): Tielectric Strength (kV/mm): -

Volume Resistivity (10^x ohm-cm): -

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1981-03-24

Last Revised: 2005-03-08 Underwriters Laboratories Inc®



IEC and ISO Test Methods

			Thickness	
Test Name	Test Method	Units	Tested (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	1.5	HB75 (ALL)
JEM HAN	(Althir Miller)		3.0	HB40 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	С	Will Sell Con	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	С	472	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)		
IEC Ball Pressure	IEC 60695-10-2	С	-	27
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	125	<u> </u>
ISO Tensile Strength	ISO 527-2	MPa	1 =	- 1
ISO Flexural Strength	ISO 178	MPa	E	112 to
ISO Tensile Impact	ISO 8256	kJ/m ²	- all 1	4h, Co.
ISO Izod Impact	ISO 180	kJ/m ²	THE COUNTY	Hiller
ISO Charpy Impact	ISO 179-2	kJ/m ²	WHI TO STEE	•
	Underwriters Laborat	tories Inc®		

The materials covered in this database are incomplete in certain constructional features or restricted in performance capabilities and are intended for use as components of complete equipment submitted for investigation rather than for direct separate installation in the field. THE FINAL ACCEPTANCE OF THE COMPONENT IS DEPENDENT UPON ITS INSTALLATION AND USE IN COMPLETE PRODUCTS SUBMITTED TO UNDERWRITERS LABORATORIES INC.

Notice of Disclaimer

1 of 1 17/7/2010 10:19